## WTA Product Testing

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## **TEST REPORT**

GEORGE LOW OF MELBOURNE 114-118 WOODLANDS DRIVE CLIENT :

BRAESIDE VIC 3195

TEST NUMBER ISSUE DATE PRINT DATE

: 7-577853-AV : 01/04/2011 : 04/04/2011

SAMPLE DESCRIPTION Clients Ref: "Hamilton" Tufted cut pile carpet Colour: Elephant (Grey)

Approximate pile height: 7.5mm

Material Specification:

Nominal pile composition: 100% Solution dyed Nylon Nominal total pile mass: 1356g/m2

Nominal backing: Primary - Synthetic Secondary - Jute

ASISO 9239.1-2003

Reaction to Fire Tests for Floorings Determination of the Burning Behaviour Part 1

using a Radiant Heat Source

Date of sample arrival:

24/02/2011 29/03/2011

Date tested: Results:

 $\begin{array}{cccc} \text{CHF (Critical Heat Flux / Critical Radiant Flux)} \\ 1 & 2 & 3 & \text{Mean} \end{array}$ 

6.2 6.8 6.2 6.4 kW/m2 Length Width 8.9 kW/m2

Smoke Value

113 134 150 132 Length % min Width % min

Observations: melting, blistering

Note: Sample was conditioned in accordance with BSEN 13238-2001 at a temperature of 23+/-2degC and Relative Humidity of 50+/-5% for a minimum of 48 hours prior to testing

Each specimen was adhered to a substrate of 6mm thick fibre reinforced cement board using GS300 adhesive and clamped prior to testing

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use

186623

© Australian Wool Testing Authority Ltd Copyright - All Rights Reserved

END OF REPORT )

PAGE 1

NATA

This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:
-Chemical Testing of Textiles & Related Products : Accreditation No. 983
-Mechanical Testing of Textiles & Related Products : Accreditation No. 985
-Heat & Temperature Measurement : Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if ammended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.

HAEL A. JACKSON B.Sc.(Hons)

LIMITEE

0204/11/06

APPROVED SIGNATORY